



شرکت تولیدی گرانول قزوین (سهامی خاص)

Ghazvin Granules Producing Co.

www.ggp.ir

Data sheet

Granule Type : GPB8570

Description : PVC compound for bedding of cables

Color : Natural

Properties	Standard and Test Method	Unit	Typical value
Hardness	ASTM D 2240(15sec)	Shore" A"	88±2
Density	ASTM D 792 / IEC 60811-1-3	gr/cm ³	1.70±0.02
Heat Stability at 200°C	VDE 0472/9.71	minute	min 60
Properties before ageing Tensile strength Elongation at break	IEC 60811-1-1	N/mm ² %	min 10 min 150

Processing Condition: As a general guide, typical processing temperature are as follows:

	zone 1	zone 2	zone 3	zone 4	head	die
max (°C)	150	170	180	180	190	200
min (°C)	130	130	140	150	160	160

Safety GPB8570 is classified as no-dangerous material.

Packaging

It is available in the form of pellets and supplied in sacking bag with a net content of 30 kgs.