



شرکت تولیدی گرانول قزوین (سهامی خاص)

Ghazvin Granules Producing Co.

www.ggp.ir

Data sheet

Granule Type :GPR65C

Description : PVC compound for automotive , door & window's profiles and gasket for extrusion and injection molding

Color : Natural and Colours

Properties	Standard and Test Method	Unit	Typical value
Hardness	ASTM D 2240(15 sec)	Shore "A"	65±2
Density	ASTM D 792 / IEC 60811-1-3	gr/cm ³	1.27±0.01
Heat Stability at 200°C	VDE 0472/9.71	minute	min 30
Tensile strength	IEC 60811-1-1	N/mm ²	min 13
Elongation at break		%	min 300

Processing Condition: As a general guide, typical processing temperature are as follows:

	zone 1	zone 2	zone 3	zone 4	head	die
max (°C)	120	130	140	150	160	160
min (°C)	110	120	130	140	150	150

Safety GPR65C is classified as no-dangerous material.

Packaging

It is available in the form of pellets and supplied in PP laminated bag with a net content of 25 kgs.

Head Office: No.64 Khorramshahr Ave., Tehran 15539- Iran, Tel:(+98 21)8193000, Fax:(+98 21)88762471 – Email info@ggp.ir