



شرکت تولیدی گرانول قزوین (سهامی خاص)

Ghazvin Granules Producing Co.

www.ggp.ir

Data sheet

Granule Type :GPS9054

Description : UV resistant PVC compound for sheathing of 90° cables

Specification : IEC 60502: PVC/ST2, BS6746:Type 9,VDE 0207:YM5

Properties	Standard and Test Method	Unit	Typical value
Hardness	ASTM D 2240(15sec)	Shore”A”	90±2
Density	ASTM D 792 / IEC 60811-1-3	gr/cm ³	1.54±0.02
Heat Stability at 200°c	VDE 0472/9.71	minute	min 90
Properties before ageing Tensile strength Elongation at break	IEC 60811-1-1	N/mm ² %	min 14 min 200
Properties after ageing “7 days at 100°c” Variation of Tensile Variation of Elongation	IEC 60811-1-2	% %	max 25 max 25
Heat shock test “1 hr at 150°c” Result to be obtained	IEC 60811-3-1	--	No Cracks
Loss of mass after ageing “7 days at 100°c”	IEC 60811-3-2	mg/cm ²	max 1.5

Processing Condition: As a general guide, typical processing temperature are as follows:

	zone 1	zone 2	zone 3	zone 4	head	die
max (°C)	160	180	190	200	210	220
min (°C)	140	150	160	160	170	170

Safety GPS9054-3BC is classified as no-dangerous material.

Packaging

It is available in the form of pellets and supplied in PP laminated bag with a net content of 25 kgs.

Head Office: No.64 Khorramshahr Ave., Tehran 15539- Iran,Tel:(+98 21)8193000, Fax:(+98 21)88762471 – Email info@ggp.ir